

Final Products Datasheet (LMF-09-04)	  Alexandria Specialty Petroleum Products Company (ASPPC)	Version Number	1
		Release Date	01/12/2022
		Revision Number	0
		Revision Date	01/12/2022

Cationic Rapid Setting Asphalt Emulsion
(ASPPC 207)

DESCRIPTION

ASPPC 207 is a rapid setting cationic asphalt emulsion (CRS-2), complies with the international standard specifications ASTM D2397.

FEATURES

- Excellent adhesion on all kinds of gravel, needs no additives.
- Can be applied easily and rapidly.
- Energy saving as it is used without heating, environmentally friendly.
- Can be applied during all weather conditions except in rainy days.

RECOMMENDED USES

- **ASPPC 207** used as tack coat and/or chip seal adhesive.
- **ASPPC 207** is ideal for Dura Patcher technology.
- **ASPPC 207** works as adhesive layer between two asphalt layers, for example between binder course and wearing course.

APPLICATION INSTRUCTIONS FOR TACK COAT

- Clean surface to be sprayed and remove any loose material.
- Spray **ASPPC 207** at a specified rate using an asphalt emulsion distributor.
- Spraying must be done uniformly and pressurized.
- **ASPPC 207** gives a dark brown color immediately after being sprayed.
- After breaking color is changed into black in about 30 minutes.
- **ASPPC 207** darkness increases with the final setting time.
- Wearing course can be laid on **ASPPC 207** after the full setting process is occurring (about 2 hrs).
- The best results of the adhering between the asphaltic layers (core test) using **ASPPC 207** is present after at least 48 hrs from laying the wearing course.

COVERAGE

- Tack coat:
 - o About 0.3 - 0.4 kg/m², depending on the nature of the substrate.
- Chip Seal:
 - o About 1.0 - 1.5 kg/m², depending on the application design.

STORAGE:

- Store **ASPPC 207** in a dry and shaded area in original packing.
- Store **ASPPC 207** in clean tanks or drums free from any chemical products or impurities, avoiding air contacts, for about four months.
- Gently stir (recycle) **ASPPC 207** once weekly for at least two hours using a pump between two storage tanks, or between the storage tank and the distributor and vice versa.

Final Products Datasheet (LMF-09-04)	  Alexandria Specialty Petroleum Products Company (ASPPC)	Version Number	1
		Release Date	01/12/2022
		Revision Number	0
		Revision Date	01/12/2022

SPECIFICATIONS

Physical Properties	Test Method	Specifications
Viscosity Saybolt Furol at 50°C, sec.	ASTMD88	100 - 400
Sieve test, %wt ^A	ASTMD6933	0.1 max
Storage stability 24 hrs, % ^A	ASTMD6930	1.0 max
Particle Charge test	ASTM D244	Positive
pH	ASTM E70	2.0 – 4.0
Distillate test:		
Oil distillate, volume of emulsion, %	ASTM D6997	3.0 max
Residue after distillation, % mass		65 min
Tests on residue from distillation:		
Penetration, 25°C, dmm	ASTMD5	100-250
Ductility, 25°C, cm	ASTM D113	40 min
Solubility in trichloroethylene, % mass	ASTMD2042	97.5 min

^A This test requirement on representative sample is waived if successful application of the material has been achieved in the field.

HEALTH & SAFETY

- **ASPPC 207** is non-toxic.
- Workers should wear protective masks, gloves and goggles during application.
- No special precautions are needed since it is water-based non-flammable material.
- **ASPPC 207** must not be swallowing.
- If swallowed, CALL PHYSICIAN IMMEDIATELY.
- In case of eye contact, open eyelids wide and flush immediately with plenty of water for at least 15 minutes. Get medical advice.

PRECAUTIONS:

- When **ASPPC 207** is in contact with air, an asphaltic skin will be formed on the surface, and this skin must be removed before reusing the product.
- **ASPPC 207** after complete drying not affected by water (re-emulsification not occur).
- Working temperature of **ASPPC 207** is 50-60 temperature; in all cases the working temperature not exceeding 65°C.
- Don't use **ASPPC 207** if the temperature during application is less than 5°C.

PACKING

- **ASPPC 207** is supplied in bulk and/or 200-liter steel drums.

DISCLAIMER

This Product Data Sheet summarizes our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this PDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. ASPPC co. does not accept any liability either directly or indirectly for any losses suffered in connection with the use or storage or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.