

ANTI-OZONE WAX (ASPPC 405)

DESCRIPTION

ASPPC 405 is a low viscosity wax blend for tire manufacturing.

RECOMMENDED USES

It is suitable for tire manufacturing. It continuously migrates to the surface of rubber components, tires providing a protective film against OZO degradation.

RECOMMENDED OPERATING TEMPERATURE

It is within a range of 75°C to 90°C.

TECHNICAL DATA

Physical Properties	Test Method	Results
Kinematic viscosity at 100°C, cSt	ASTM D445	5 typical
Congeaing point, °C	ASTM D938	60-67
Needle penetration at 25°C, (0.1mm)	ASTM D1321	12 - 25
Oil content, %wt	ASTM D721	2 max
Ash, wt%	ASTM D482	0.1 max
Color ASTM	ASTM D6045	2 max
Odor	-----	Odorless

STORAGE

24 months when stored in a dry area, under ambient conditions, ideally between 10°C and 30°C. Keep cases closed to avoid contamination. Rotate stock.

PACKAGING

Pastilles in bags 20 or 25 kg net weight.